

# CTM POTTERS SUPPLIES

---

## SPEC SHEET

### CUPROUS OXIDE

Appearance: -	Red Powder
Stability: -	The cuprous Oxide will lose not more than 2% of its total reducing power when exposed to an atmosphere of air with relative humidity of 95% at 100°F for a period of 72 hours.
Bulk Density: -	1.3 – 1.4g/ml

### Chemical Specification

<b>Cuprous Oxide (Cu<sub>2</sub>O)</b>	<b>99%</b>
<b>Total Copper</b>	<b>87%</b>
<b>Total reducing Power (T.R.P)</b>	<b>99%</b>
<b>Metallic Copper</b>	<b>0.014%</b>
<b>Stability Loss</b>	<b>0.24%</b>